



# Chek-Stop Lumber Coating

## General Properties

A high solids, high build coating designed to reduce checking (splitting) on the ends of milled lumber or logs. This is a fast drying, solvent-based product, which allows for applications under adverse weather conditions.

## Recommended Uses

Use on the ends of milled lumber. Best results are obtained when Chek-Stop is applied immediately after lumber is milled.

## Product Information

<b>GENERIC TYPE</b>	Hydrocarbon Wax
<b>PIGMENT TYPE</b>	Lightfast
<b>COLOR</b>	77061 Clear, 77065 Red, 77068 Tan; Custom colors are available
<b>BASES</b>	N/A
<b>FINISH</b>	Low Sheen
<b>AVERAGE VOLUME SOLIDS</b>	53%
<b>AVERAGE WEIGHT SOLIDS</b>	71%

<b>RECOMMENDED FILM THICKNESS</b>	Wet: 20 - 25 mils Dry: 10 - 13 mils See your Cloverdale Representative for project recommendations.
<b>THEORETICAL COVERAGE</b>	850 ft <sup>2</sup> /gal @ 1 mil (25 microns) DFT 20.8 m <sup>2</sup> /L @ 1 mil (25 microns) DFT Actual coverage may vary depending on substrate and application methods.
<b>VISCOSITY</b>	60 K.U.
<b>TEMPERATURE RESISTANCE (DRY)</b>	71°C (160°F)
<b>V.O.C. AS APPLIED</b>	Less than 365 g/L (3.04 lbs/gal)
<b>THINNER</b>	78011 Xylene

## Methods of Application

<b>AIRLESS SPRAY</b>	Speeflo Ensign 30:1 with tip sizes .017" - .031" or equivalent
<b>H.V.L.P.</b>	Not recommended
<b>CONVENTIONAL</b>	Not recommended
<b>BRUSH / ROLLER</b>	Brushing is limited to touch-up only

**Drying Time** - Temperature, Relative Humidity, and Film Thickness will affect dry and re-coat times.

Substrate Temperature	Touch Dry	Hard Dry	Minimum	Overcoat Interval	
				Maximum	Normal
25°C (77°F)	1 hour	1 hour	N/A	N/A	N/A

**Recommended Primer**

Self Priming

**Surface Preparation**

Surfaces must be clean and free of excess moisture and contaminants such as sawdust and dirt. Sapstain chemical, if used, should be applied prior to the Chek-Stop.

**Limitations**

For use as a single-coat application only. Not intended for use as a primer or part of multi-coat paint system.

**Mixing Instructions**

Mix well before using. Do not thin. Use as supplied.

**Safety Precautions**

This product is for industrial use only. **Refer to Material Safety Data Sheet for proper health and safety information.**

**Storage and Handling**

<b>FLASH POINT</b>	-7°C (19°F) T.C.C.
<b>PRODUCT WEIGHT</b>	10.7 lbs/gal (container extra)
<b>STORAGE</b>	Store in heated location: See your Cloverdale Paint Representative.
<b>PACKAGE SIZE</b>	55 gallon drum, tote tank

Some package sizes or colors may be by special order only. Please check with your Cloverdale Representative when ordering.

**Warranty Disclaimer**

Cloverdale Paint manufactures quality products. In the event that this product is defective or in any way unsuitable for the application for which it is sold, Cloverdale Paint Inc. will replace the product free of charge. The warranty provided by this data sheet is the only warranty or guarantee of quality made in respect of this product by Cloverdale Paint Inc. By purchasing this product the customer accepts this warranty in lieu of all others, and waives all claims to any other remedy arising from any warranty or guarantee of quality, whether such warranty or guarantee of quality was made expressly to the customer or implied by any applicable law.

Check for recent amendments to this data sheet at [www.cloverdalepaint.com/html/catalog\\_recent\\_ir.asp](http://www.cloverdalepaint.com/html/catalog_recent_ir.asp)

**Cloverdale Paint Inc.**

6950 King George Highway, Surrey, British Columbia, Canada V3W 4Z1  
Web Site: [www.cloverdalepaint.com](http://www.cloverdalepaint.com) Email: [helpdesk@cloverdalepaint.com](mailto:helpdesk@cloverdalepaint.com)  
Phone: 604 596 6261 Fax: 604 597 2677