



# Presto White 50

Post Catalysed Lacquer

## General Properties

Presto White is a 2 component, multi-resin, catalysed lacquer designed for all types of interior use. It provides a smooth hard wearing surface that is resistant to alcohol, water, grease and the usual household chemicals.

## Recommended Uses

For use on interior wood surfaces where a high degree of durability and hardness is required. Excellent for residential and institutional cabinetry, doors, tables and related millwork. Performs very well under exposure to mild chemicals and water.

## Product Information

**GENERIC TYPE**  
Modified Lacquer

**FINISH**  
50 units @ 60°

**COLOR**  
White

**BASES**  
N/A

**AVERAGE VOLUME SOLIDS**  
26%

**AVERAGE WEIGHT SOLIDS**  
39.6%

**VISCOSITY @ 25°C (77°F)**  
45-48" Z#2

**RECOMMENDED FILM THICKNESS**  
Dry: 3 mils

**THEORETICAL COVERAGE**  
12-14 sq m/l (417 sq. ft./gal)  
at 1 mil dry and 100% transfer efficiency

**MIXED RATIO**  
requires 10% 48 999-089

**POT LIFE**  
8 hours

**HAPS**  
1.52 lbs. haps/lbs solids

**V.O.C. MIXED GALLON**  
636 g/L

**THINNER**  
78019 Lacquer Thinner

## Methods of Application

**AIRLESS SPRAY**      suitable

**H.V.L.P.**              suitable

**CONVENTIONAL**      suitable

**BRUSH / ROLLER**      For professional spray application only, not suitable for on-site brush and roll projects.

**Drying Time** - Temperature, Relative Humidity, and Film Thickness will affect dry and re-coat times.

Substrate Temperature	Touch Dry	To Sand	Stack Time	Overcoat Interval	
				Minimum	Maximum
20°C (68°F)	15 minutes	35 minutes	6 hours	N/A	N/A

**Recommended Primer Sealer**

Use post catalyzed primer, 220-223, 220-214

**Surface Preparation**

Wood substrate should be sanded with 120, 150 or 180 grit paper prior to staining or coating. When re-coating, the sealer or previous coat must be sanded within 8 hours.

**Limitations**

Primer systems used under acid cured products should be acid stable. Product cannot be used on metal, oil or cellulose lacquers. Presto must not be polluted with oil, varnish or the like and cannot be sanded with steel wool between coats. Shelf life 12 months un-opened.

**Mixing Instructions**

Agitate material before use and during the addition of hardener.

**Safety Precautions**

This product is for industrial use only. **Refer to Material Safety Data Sheet for proper health and safety information.**

**Storage and Handling**

<b>FLASH POINT</b>	4°C
<b>PRODUCT WEIGHT</b>	8.66 lbs/gal +/- (container extra)
<b>STORAGE</b>	Cool, dry, secure location. See your Cloverdale Paint Representative.
<b>PACKAGE SIZE</b>	3.79L, 18L and 205L

Some package sizes or colors may be by special order only. Please check with your Cloverdale Representative when ordering.

**Warranty Disclaimer**

Cloverdale Paint manufactures quality products. In the event that this product is defective or in any way unsuitable for the application for which it is sold, Cloverdale Paint Inc. will replace the product free of charge. The warranty provided by this data sheet is the only warranty or guarantee of quality made in respect of this product by Cloverdale Paint Inc. By purchasing this product the customer accepts this warranty in lieu of all others, and waives all claims to any other remedy arising from any warranty or guarantee of quality, whether such warranty or guarantee of quality was made expressly to the customer or implied by any applicable law.

**Cloverdale Paint****Cloverdale Paint Inc.**

**6950 King George Highway, Surrey, British Columbia, Canada V3W 4Z1**  
**Web Site:** [www.cloverdalepaint.com](http://www.cloverdalepaint.com) **Email:** [helpdesk@cloverdalepaint.com](mailto:helpdesk@cloverdalepaint.com)  
**Phone:** 604 596 6261 **Fax:** 604 597 2677